

TECHNICAL DATA SHEET

HYDROCARBON RESIN SK-120

Typical Properties

Softening Point, (R&B), °C	120±5	(ASTM E28)
Color, Gardner, 50% resin solids in toluene	10 Max.	(ASTM D1544)
Bromine Number, Br cg/g	35 Max.	(ASTM D1159)
Acid Value, KOH mg/g	0.1 Max.	(ASTM D664)
Specific Gravity, @25°C	1.05~1.10	(ASTM D71)

