

SL4071X75

Epoxy Resin solution

SL4071 X 75 is a medium molecular weight epoxy resin based on Bisphenol A as solvent cut 75% in Xylene.

Specific Key Data	Property	Value	Test method
	Appearance	Clear, no contamination	JCTM 003
	Color (Gardner)	3 max	ASTM D-1544
	Epoxy Value (supplied)	1.42 - 1.67 eq/Kg	ASTM D-1652
	Weight per Epoxide (supplied)	600 - 700 g/eq	ASTM D-1652
	Solid Content	74 - 76%	JCTM 0097
	Viscosity at 25°C (77°F)	5000 - 10000 mPas	ISO 12058-1
Typical Key Data	Density at 25°C	~ 1.08 g/cm ³	ISO 1675
	Flash point, closed cup	31°C	DIN 53213

INNOVATIVE
TRADING SOLUTIONS FZ LLC
DRIVEN BY PASSION RUN FOR SUCCESS